



# Implication of Atmospheric Wetness Levels on Corrosion at a Coating Defect during Accelerated Testing

James F. Dante  
Southwest Research Institute

ASETS Defense  
8/28/2012

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE <b>28 AUG 2012</b>		2. REPORT TYPE		3. DATES COVERED <b>00-00-2012 to 00-00-2012</b>	
4. TITLE AND SUBTITLE <b>Implication of Atmospheric Wetness Levels on Corrosion at a Coating Defect during Accelerated Testing</b>				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) <b>Southwest Research Institute, 6220 Culebra Rd, San Antonio, TX, 78238-5166</b>				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT <b>Approved for public release; distribution unlimited</b>					
13. SUPPLEMENTARY NOTES <b>ASETSDefense 2012: Sustainable Surface Engineering for Aerospace and Defense Workshop, August 27-30, 2012, San Diego, CA. Sponsored by SERDP/ESTCP.</b>					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT <b>Same as Report (SAR)</b>	18. NUMBER OF PAGES <b>19</b>	19a. NAME OF RESPONSIBLE PERSON
a. REPORT <b>unclassified</b>	b. ABSTRACT <b>unclassified</b>	c. THIS PAGE <b>unclassified</b>			

# Background

- SERDP program to develop improved accelerated corrosion test
- Many accelerated environmental tests exist
  - Developed by applying reasonable environmental conditions and ensuring resultant corrosion damage of a test system is realistic: **may or may not “excite” specific operational failure modes in other systems**
- Approach to new accelerated corrosion test
  - Thoughtful consideration of appropriate sample design
  - Make use of scientific understanding of corrosion mechanisms to develop exposure test cycle parameters

# Outline

- Objectives
- Atmospheric corrosion
- Testing Approach
- Effect of RH on corrosion of steel
- Effect of inhibitor addition on coated steel
- Summary and future work

# Technical Objective

- **Objective**

- Develop an understanding of how RH affect corrosion rate and perturbations in corrosion rate with inhibited coatings

- Why is understanding of RH effect important?

- SAEJ2334 shows best correlations with field. Performed under wet bottom RH conditions (NOT FOG)


- Cyclic conditions lead to different corrosion modes

- SCC observed at salt deliquescence


- Realistic conditions failure modes must be replicated in appropriate accelerated test methods

# Atmospheric Corrosion



- Corrosion processes in the atmosphere are controlled by a thin film electrolyte layer on a metal substrate
- The electrolyte layer composition is controlled by
  - Atmospheric constituents (aerosols and gasses)
  - Relative Humidity (RH) and temperature
  - The presence of inhibitors in or galvanic interactions with coatings



# Experimental Approach



- Corrosion (anodic site) and reduction (cathodic site) occur at the same rate
- Electrons flow from anode to cathode
- Multiple isolated anodes or cathodes develop
- Measure current at each electrode gives corrosion rate at the corrosion potential




# Experimental Procedure

- 100 electrode (250 micron) multi-electrode probe fabricated using 1018 carbon steel
- $\sim 10\text{mg}/\text{cm}^2$  of NaCl placed over electrode elements (factor of 10 – 100 greater than outdoors)
- Atmospheric chamber used to control RH and temp
- Exposed under different RH conditions for 2.5 hour followed by reducing RH to 40%





# Multi-Electrode Measurements

- chamber assembled to control iso-humidity conditions
- Anodic and cathodic regions form on multi-electrode probe




# Measurements at Iso-Humidity



- Total anodic current vs. time shows different corrosion rates over time
  - < 70% is likely flash rust (short duration, electrolyte supports rust formation near 60% RH)
  - Anodic current peaks during wetting and drying
- Integration of current vs. time gives charge passed.
  - For NaCl covered surface and RH > 70%, , passed charge is similar to bulk liquid exposure

# Measurements in Cyclic Humidity

- How does wetting and drying affect corrosion processes?
- Tests performed in an AutoTechnology accelerated corrosion test chamber
- RH cycled between high and low values. Temp = 30°C




Parallel plate wetness probe



MMA and RH probes



# Measurements in Cyclic Humidity



- Anodic current flows when RH is well below 40% and even as low as 15% during drying (efflorescence)
- Peaks in total anodic current are observed during wetting and drying
  - 60% - 65% = Thin film electrolyte behavior where initial high corrosion rate from oxygen availability followed by protective layer formation and decreasing corrosion rate
  - Above DRH = bulk electrolyte behavior + dissolved NaCl creating non-protective rust layer



# Volume of Adsorbed Water

- Work by Dante and Kelly (1993) calculated adsorbed water onto Au
- Assuming Au and steel adsorption is similar and  $30\text{nl}/\text{cm}^2/\text{monolayer}$  of water, can calculate volume of adsorbed moisture with salt
- OLI calculations used to calculate volume of water with NaCl deliquescence
- Corrosion of Steel can occur at 60% RH, would expect some protection since NaCl is not dissolved
- Above DRH, bulk water accumulation so would expect non-protective oxide




# Hypothesis – Protection at a Scribe

Continuous salt fog




Dilute cyclic salt fog




- Ability to protect substrate at a coating defect depends on connectivity between defect and mode of inhibition
- Moisture can promote inhibitor migration in the coating. For a given test method, wet and dry times will influence inhibitor mobility, and thus corrosion rate

# Hypothesis – Protection at a Scribe


- For coated systems, what is the controlling process in corrosion failure at a scribe?
  - Corrosion rate of the substrate as a function of RH
  - Inhibitor mobility (or galvanic connectivity) (red dots are theoretical)



# Simulation of Painted Surfaces





- Electrode surface painted leaving 20 electrodes (i.e. 2 rows) uncovered
- $\frac{1}{2}$ " o-ring placed over electrodes and salt deposited







# Effect of Inhibitor Leaching



- Inhibitors effect only below DRH
- Inhibitors suppresses the 60% RH peak for steel



# Effect of Inhibitor Leaching



- Electrochemical potentiodynamic scans performed in NaCl + 0.001 M NaCl dichromate
- As NaCl decreases, cathodic current density increases
- Therefore, RH increases (NaCl decreases), total charge passed increases

# Summary and Implications for Accelerated Testing

- Original hypothesis of chromate mobility decreasing with decreasing RH is not supported by the data
  - Component corrosion in cyclic environments controlled by galvanic interactions?
  - Need to determine what RH range results in decoupling of steel and aluminum
- Inhibitors protect against corrosion at 60% - 65% RH (flash rust) on steel
  - Short lived event that is likely inconsequential

# Continuing Work

- Ongoing testing to define drying time as a function of
  - Time when  $RH > DRH$
  - Drying time at differing  $RH$  values  $< DRH$
- Testing using Aluminum electrodes